














SAVUTE PRODUCT SPECIFICATION

Savute Matt Rectified Glazed Porcelain 600 x 1200mm
 Pressed Ceramic Tiles International Norm ISO 13006-10545/98
 GROUP: B1b

| No. | Icon | Test item | Unit | Requirements of Standard | | Specifica- tion | Requirement |
|-----|---|-------------------------------|-----------|--|-------|--------------------|----------------------------------|
| 1 |  | Dimensional variation | (%) | length of side | ±0.6 | < 0.6 | Qualified |
| 2 |  | Side straightness | (%) | ± 0.5 | | < 0.5 | Qualified |
| 3 |  | Squareness | (%) | ± 0.5 | | < 0.5 | Qualified |
| 4 |  | Surface flatness | (%) | Center curvature degree | ± 0.5 | < 0.5 | Qualified |
| | | | | Warping degree | ± 0.5 | < 0.5 | Qualified |
| | | | | Side curvature degree | ± 0.5 | < 0.5 | Qualified |
| 5 |  | Surface quality | — | Sighting vertically at a distance of 0.8 meter away from the tile no defect on surface is observed in at least 95% of the tile | | conformed | Qualified |
| 6 |  | Water absorption | (%) | 0.5% ≤ E ≤ 3% | | conformed | Qualified |
| 7 |  | Breaking strength | N | When thickness ≥ 7.5mm the Average value ≥ 1300 | | > 1300 | Qualified |
| 8 |  | Rupture modulus | Mpa | Average value ≥ 35 individual ≥ 32 | | > 35 > 32 | Qualified |
| 9 |  | Hardness | MOHS | Mohs Scale | | 6 | Qualified |
| 10 |  | Frost resistance | — | No cracking after test | | conformed | Qualified |
| 11 |  | Resistance to acids & alkalis | — | not less than grade GB | | Grade GA | Qualified |
| 12 |  | Chemical resistance | — | not less than grade GB | | Grade GA | Qualified |
| 13 |  | Slip resistance | R DCoF | Slip rating test DCoF: 0.42 | | R11 > 0.42 | Exterior only Matt & exterior |