















	Proprietà fisico-chimiche physical chemical properties Propriétés physico chimiques Physisch chemische	Metodo di prova Standard of test Norme du test Testnorm	DECAPE'
	Dimensioni / Dimensions / Dimensions / Abmessungen Lunghezza e Larghezza Length and Width Longuer et Largeur Länge und Breite	ISO10545-2 ± 0,3% max	 ± 0,3% max
	Spessore Thickness Epaisseur Stärke	 ± 5% max	 ± 5% max
	Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme	ISO 10545 -3 ≤ 0,5%	 ≥ 0,1%
	Resistenza al gelo Frost resistance Résistance au gel Frostbestandigkeit	ISO 10545 -12	Resistente Resistant Résistant Widerstandfahig
	Resistenza agli sbalzi termici Resistance to Thermal shock Résistance aux écarts de température Temperaturwechselbestandigkeit	ISO 10545 - 9	Resistente Resistant Résistant Widerstandfahig
	Variazione di tono Shade variations Variations de nuance Tonvariation		 V3 MODERATA VARIAZIONE MODERATE VARIATION VARIATION MODÉRÉE MÄßIGE ABWEICHUNG
	Resistenza all'abrasione Resistance to abrasion Résistance à l'abrasion Bestaendigheit gegen abrieb	ISO 10545 - 7	Classe 5 Class 5 Classe 5 Gruppe 5
	Resistenza alle macchie Resistance to stains Résistance aux taches Fleckenbestandigkeit	ISO 10545 - 14	Classe 5 Class 5 Classe 5 Gruppe 5
	Resistenza ai prodotti chimici di uso domestico Resistance to surface to househod chemicals Résistance aux produits chimiques ménagers Beständigkeit gegen haushaltschemikalien	ISO 10545 - 13	Classe A Class A Classe A Gruppe A
	Resistenza agli acidi e alle basi a bassa concentrazione resistance to low concentrations of acid and bases Résistance aux acides et aux bases à faible concentration Beständigkeit gegen niedrig konzentrierte säuren und basen		Classe LA -HA Class LA -HA Classe LA -HA Gruppe LA -HA
	Resistenza alla flessione Modulo di rottura/Carico di rottura Bending strength Modulus of rupture/Braking of rupture Résistance à la flexion Module de rupture/Charge de rupture Biegezugfestigkeit Bruchmodul/Last	ISO 10545 - 4 R ≥ 35 N/mm2 S ≥ 1300 N	R = 53 N/mm2 S = 2685 N

	Caratteristiche antiscivolo/Coefficiente d'attrito statico Anti-slip properties/Static coefficient of friction Caractéristiques antidérapantes/Coefficient de frottement statique Anti-Rutsch eigenschaften/Haftreibungskoeffizient	DIN 51130	R 10
		B.C.R.A. 0,40 ≤ < 0,70 Attrito soddisfacente	0.48/0,52
	Ignifugo Fire resistant Résistant au feu Feuerfest		Resistente Resistant Résistant Widerstandfähig
	Igienico e facilmente pulibile Hygienic and easy to clean Sain et facile à nettoyer Hygienisch und einfach zu reinigen		Conforme Compliant Conforme Konform