

















	Proprietà fisico-chimiche physical chemical properties Propriétés physico chimiques Physisch chemische	Metodo di prova Standard of test Norme du test Testnorm	DOLOMIA LCR
	Dimensioni / Dimensions / Dimensions / Abmessungen Lunghezza e Larghezza Length and Width Longuer et Largeur Länge und Breite	ISO10545-2 ± 0,3% max	 ± 0,3% max
	Spessore Thickness Epaisseur Stärke	 ± 5% max	 ± 5% max
	Assorbimento d'acqua Water absorption Absorption d'eau Wasseraufnahme	ISO 10545 -3 ≤ 0,5%	Conforme Compliant Conforme Konform
	Resistenza al gelo Frost resistance Rèsistance au gel Frostbeständigkeit	ISO 10545 -12	Resistente Resistant Rèsistant Widerstandfähig
	Resistenza agli sbalzi termici Resistance to Thermal shock Rèsistance aux écarts de température Temperaturwechselbeständigkeit	ISO 10545 - 9	Resistente Resistant Rèsistant Widerstandfähig
	Variazione di tono Shade variations Variations de nuance Tonvariation		 V4 V4/RANDOM Forte stonalizzazione Substantial variations Effet dénuancé très accentué Starkes Farbspiel
	Resistenza all'abrasione Resistance to abrasion Rèsistance à l'abrasion Bestaendigkeit gegen abrieb	ISO 10545 - 7	Classe 4 Class 4 Classe 4 Gruppe 4
	Resistenza abrasione profonda Deep abrasion resistance Resistance a l'usura en profondeur Tiefen-abriebbetandigkeit	ISO 10545-6 ≤ 175 N/mm	Conforme Compliant Conforme Konform
	Resistenza alle macchie Resistance to stains Rèsistance aux taches Fleckenbeständigkeit	ISO 10545 - 14	Classe 5 Class 5 Classe 5 Gruppe 5
	Resistenza ai prodotti chimici di uso domestico Resistance to surface to househod chemicals Rèsistance aux produits chimiques ménagers Beständigkeit gegen haushaltschemikalien		Classe A Class A Classe A Gruppe A
	Resistenza agli acidi e alle basi a bassa concentrazione resistance to low concentrations of acid and bases Rèsistance aux acides et aux bases à faible concentration Beständigkeit gegen niedrig konzentrierte säuren und basen	ISO 10545 - 13	Classe LA -HA Class LA -HA Classe LA -HA Gruppe LA -HA

	<p>Resistenza alla flessione Modulo di rottura/Carico di rottura Bending strength Modulus of rupture/Braking of rupture Résistance à la flexion Module de rupture/Charge de rupture Biegezugfestigkeit Bruchmodul/Last</p>	ISO 10545 - 4 $R \geq 35 \text{ N/mm}^2$ S $\geq 1300 \text{ N}$	$R = 52,3 \text{ N/mm}^2$ S $= 2672,8 \text{ N}$
	<p>Fattore di resistenza alla scivolosità Anm-skeed resistance grade Gre' de resistance à la glissance Rutschfestigkeit</p>	B.C.R.A. $0,40 \leq$	0,59
	<p>Fattore di resistenza alla scivolosità Anm-skeed resistance grade Gre' de resistance à la glissance Rutschfestigkeit</p>	ANSI A 326.3:2022 $0,42 \leq$	0,44 / 0,92
	<p>Ignifugo Fire resistant Résistant au feu Feuerfest</p>		<p>Resistente Resistant Résistant Widerstandfähig</p>
	<p>Igienico e facilmente pulibile Hygienic and easy to clean Sain et facile à nettoyer Hygienisch und einfach zu reinigen</p>		<p>Conforme Compliant Conforme Konform</p>