



























6 mm / COLOURED BODY PORCELAIN STONEWARE

	E.N. 14411-ISO 13006 . Appendix G. Group BIa. GL	Test method	Reference value	Declared value
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	>0,42 wet MATTE
	Release of hazardous substances	DM-1-2-2007-Reg-CE-1935-2004	Valore dichiarato per superfici gl con impieghi su piani di lavoro / Declared value for gl surfaces used on worktops / valeur déclarée Pour surfaces gl utilisées sur plans de travail / angegebener wert für Gl oberflächen zum gebrauch als arbeitsplatten / valor declarado Para acabados gl utilizados para superficies de trabajo / заявленное Значение для глазурованных поверхностей, с использованием на рабочих столах	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ (± 1 mm)	$\pm 0,15\%$
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ($\pm 1,5$ mm)	$\pm 0,2\%$
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,4\%$ ($\pm 1,8$ mm)	$\pm 0,2\%$
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ($\pm 0,8$ mm)	$\pm 0,1\%$
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	$\pm 5\%$ ($\pm 0,5$ mm)	$\pm 5\%$
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	$E \leq 0,5\%$	average value 0,08%
	Bending strength in N/mm ²	ISO-10545-4	>35 N/mm ²	average value 52 N/mm ²
	Breaking strength in N (thickness < 7,5 mm)	ISO-10545-4	≥ 700 Newton	average value 1350 N
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur /	ILLUSION: Cl. 4

			Entsprechend der Herstellerangaben / Tal como declara el fabricante	
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	SYMPHONIE: Cl. 3
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GRIS: Cl.3 MATTE - Cl. 2 GLOSSY
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	BROWN RIVER: Cl. 2
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	TROPICAL: Cl. 2
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	CRÈME: Cl. 4
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	RENOIR: Cl. 2
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Glaze crazing resistance	ISO-10545-11	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLB GLOSSY
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLA MATTE
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	GB minimo / GB minimum / GB minimum / GB mindestens / GB mínimo	GA
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 4-5 MATTE
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 3-4 GLOSSY















Note:






-

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

Copyright © 2013 Florim S.p.A. SB a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 PI/CF 01265320364

9 mm / COLOURED BODY PORCELAIN STONEWARE

	E.N. 14411-ISO 13006 . Appendix G. Group BIa. GL	Test method	Reference value	Declared value
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	>0,42 wet MATTE
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadro ISO 13006 - ±0,3% (±1 mm)	±0,15%
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadro ISO 13006 - ±0,3% (±1,5 mm)	±0,2%
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadro ISO 13006 - ±0,4% (±1,8 mm)	±0,35%
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadro ISO 13006 - ±0,3% (±0,8 mm)	±0,1%
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	±5% (±0,5 mm)	±5%
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	E≤0,5%	average value 0,08%
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 50 N/mm2
	Breaking strength in N (thickness >= 7,5 mm)	ISO-10545-4	≥1300 Newton	average value 2200 N
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 4
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Glaze crazing resistance	ISO-10545-11	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ

	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLB GLOSSY
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLA MATTE
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	GB minimo / GB minimum / GB minimum / GB mindestens / GB minimo	GA
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 4-5 MATTE
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 mínimo	Cl. 4 GLOSSY

Note:

-

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

Copyright © 2013 Florim S.p.A. SB a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 PI/CF 01265320364